


General			
Weight	590 ± 10% g/m²		
Width	1.37 m		
Topcoat			
Roll Length	31.1 m		
Composition	PVC		
Gauge	1.05 ± 10% mm		
Backing			
Description	Hi-Loft <sup>2™</sup>		
Weight	130 g/m² - ASTM D751		
Type	Polyester		
Flame Retardancy			
FMVSS 302		NFPA 260 - Cover Fabric - Class I	
UFAC Fabric - Class I		CAL TB 117-2013	

This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.

Other Attributes				
Anti Static	ASTM D257		Bacterial Resistant	AATCC 147
Mildew Resistant	No Growth (NG)		Mildew Resistance Method	ASTM G21
Pink Stain Resistant	ASTM E1428		Sulfide Stain Resistance	FISHER BODY TM 31-12
Additional Tests				
Tensile Strength Test - ASTM D751 / CFFA-17				
Lbf(Min.)	Warp		121	
	Fill		72	
Elongation At Break Test - ASTM D751 / CFFA-17				
%(Ave.)	Warp		67	
	Fill		159	
Tear Strength - Tongue Method Test - ASTM D751 / CFFA-16b				
Lbf(Min.)	Warp		8.1	
	Fill		6.9	
Stitching Strength Test - DIN 54301				
Lbf(Min.)	Warp		12	
	Fill		8.6	
Adhesion Test - ASTM D751 / CFFA-3				
Lbf/In(Min.)	Warp		3.3	
	Fill		3.3	
Abrasion Resistant II Test - ASTM D4157 / CFFA-1a				
WYZENBEEK	100,000 cycles		4.0	
Flex Resistance Test - ASTM D2097 / CFFA-10				
cycles	Warp		30,000 = Passes	
	Fill		30,000 = Passes	
UV stability Test				
Quv	ASTM D-4329 / CFFA-2 c2		Cal≥4 650 Hours = Passes	
Weather o Meter	ISO 105-B04 - Colour fastness to artificial weathering		Rating/Cal ≥ 4 (Passes) - Grey Scale - 1,000 Hours	
Cold Crack Test				
CFFA-6a	Passes -10 °F			
Blocking Test				
CFFA-4	No.1 - No Blocking ; No Adhesion			

Note: The data correspond to minimum results of the statistical analysis. The information included in the specification is subject to change.  
The indicated data corresponding to the material's physical characteristics are results of test conducted under standard procedures and are subject to variation. We therefore recommend our customers to evaluate the material with regard to the specific requirements and application(s) before specifying. For additional information, please contact your sales representative.  
These terms and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.  
Spradling group does not assume any responsibility for any damages resulting from improper applications.  
Spradling group does not guarantee exact color matches as slight variations in production and stock may occur, as such lot separations is suggested.  
Spradling group reserves the right to modify technical sheets without notification.