

General			
Weight	660 ± 10% None		
Width	1.37 m		
Topcoat	ACRYLIC		
Roll Length	27.4 m		
Composition	PVC		
Gauge	1.00 ± 10% mm		
Backing			
Description	Standard Polyester		
Weight	80 g/m ² - ASTM D751		
Type	Polyester		
Flame Retardancy			
FMVSS 302		IMO FTP 2010 Code MSC.307(88), Part 8, 3.1 & 3.2	
NFPA 260 - Cover Fabric - Class I		UFAC Fabric - Class I	
CAL TB 117-2013			

This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.

Other Attributes			
Anti Static	ASTM D257	Bacterial Resistant	AATCC 147
Mildew Resistant	No Growth (NG)	Mildew Resistance Method	ASTM G21
Pink Stain Resistant	ASTM E1428	Sulfide Stain Resistance	FISHER BODY TM 31-12
Water Resistant	Yes	Formaldehyde Free	Yes
Cleanable	Yes	Bleach Cleanable (1:9)	Yes
No Heavy Metals	Yes		

Additional Tests			
Tensile Strength Test - ASTM D751 / CFFA-17			
Lbf(Min.)	Warp		92
	Fill		69
Elongation At Break Test - ASTM D751 / CFFA-17			
% (Ave.)	Warp		73
	Fill		143
Stitching Strength Test - DIN 54301			
Lbf(Min.)	Warp		10
	Fill		8.3
Adhesion Test - ASTM D751 / CFFA-3			
Lbf/In(Min.)	Warp		3.3
	Fill		3.3
Abrasion Resistant II Test - ASTM D4157 / CFFA-1a			
WYZENBEEK			50,000 cycles No appreciable wear
Crocking Resistant I Test (CFFA - 7)			
-----	Wet		Excellent
	Dry		Excellent
Flex Resistance Test - ASTM D2097 / CFFA-10			
cycles	Warp		30,000
	Fill		30,000
UV stability Test			
Quv	ASTM D-4329 / CFFA-2 c2		Cal ≥ 4 650 Hours = Passes
Weather o Meter	ISO 105-B04 - Colour fastness to artificial weathering		Rating/Cal ≥ 4 (Passes) - Grey Scale - 1,000 Hours
Cold Crack Test			
CFFA-6a			-10 °F
Blocking Test			
CFFA-4			No.1 - No Blocking ; No Adhesion

Note: The data correspond to minimum results of the statistical analysis. The information included in the specification is subject to change.

The indicated data corresponding to the material's physical characteristics are results of test conducted under standard procedures and are subject to variation. We therefore recommend our customers to evaluate the material with regard to the specific requirements and application(s) before specifying. For additional information, please contact your sales representative.

These terms and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.

Spradling group does not assume any responsibility for any damages resulting from improper applications.

Spradling group does not guarantee exact color matches as slight variations in production and stock may occur, as such lot separations is suggested.

Spradling group reserves the right to modify technical sheets without notification.

For a better experience, we recommend opening the file directly in a PDF viewer, and not in the browser.

Date: April 26, 2019